

PRODUCT DATA SHEET

Date: 04/26/2024

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

PrimeScan® 90 ** B-82 ** 50# liner

Item#: 0049708

Basis Weight:

Caliper:

Facestock: PrimeScan® 90

A polyolefin-based, clay-coated, 90-micron-thick film designed to be compatible with most common impact, and many non-impact, print methods. It is waterproof, tear-resistant, grease resistant, and resists temperature fluctuations. It will die cut and fold easily and is compatible with hot foil stamping and embossing. Similar to paper, PrimeScan 90 is a film with memory. To minimize pickers curl in hand-applied applications, remove the liner from the facestock when possible (rather than face from liner). Outdoor durability is up to 18 months, depending on climate and exposure conditions.

Typical Value

46 #/3300 ft² 3.6 mils

 Tensile MD/CD:
 6670 / 5510 PSI

 Elongation @ Break MD/TD:
 120 / 110%

 Opacity:
 90%

Adhesive: **B-82** A general purpose hot melt adhesive with excellent quick-stick properties and

long-term adhesion to a broad range of surfaces.

Typical Value

Coat Weight: $14 \#/3300 \text{ ft}^2$ Coat Weight: 20.72 grams/m^2

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 60 Loop Tack, oz.: 94

Service Temperature: -50 to 150 °F Minimum Application Temperature: 40 °F Shear (1000g): 445 minutes Release Liner: 50# liner A bleached, calendered liner featuring higher tensile and tear properties than the

40# liner, making it an excellent liner for perforating, fan-folding, and edge-

punching.

Typical Value

Basis Weight: $53 \#/3000 \text{ ft}^2$ Caliper: 3.2 mils Tensile MD/CD: 48 / 26 #/inch Tear MD/CD: 45 / 51 grams

Opacity: 74%

Total Product Caliper: 7.4 mils

Product Basis Weight Per MMSI: 249.05 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 10/27/2021