



## PRODUCT DATA SHEET

Date: 05/09/2024

**Spinnaker**  
550 Summit Avenue  
Troy, Oh 45373  
800 543-9452

### 4.0 mil TC Matte White Polypropylene \*\* SFA™ (2020) \*\* 40# liner

Item#: 0049232

#### ----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	4"	3"

Facestock: **4.0 mil TC Matte White Polypropylene**

A white, clay-coated, biaxially-oriented polypropylene film for use in a variety of printing and converting applications where durability, strength, and superior printability are key. One side is matte with a special print-receptive coating and the other is a satin gloss. Its key attribute is excellent thermal transfer printability. It will not tear unless an edge is nicked. Outdoor durability is about 3 to 6 months, depending on climatic conditions.

#### Typical Value

Basis Weight:	55.2 #/3300 ft <sup>2</sup>
Caliper:	3.74 mils
Tensile MD/CD:	11,352 / 17028 PSI
Elongation @ Break MD/TD:	130 / 52%
Gloss:	15 / 115%
Opacity:	88%

Adhesive: **SFA™ (2020)**

A clear, general purpose, emulsion acrylic permanent adhesive designed for applications with film facestocks. SFA exhibits excellent ultimate adhesion to polyethylene, polypropylene and glass. Well suited for small, cylindrical labeling. Limited testing shows this adhesive to be glove friendly, but application testing is recommended.

#### Typical Value

Coat Weight:	13 #/3300 ft <sup>2</sup>
Coat Weight:	19.24 grams/m <sup>2</sup>
Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	32
Loop Tack, oz.:	50
Service Temperature:	-40 to 240 °F
Minimum Application Temperature:	15 °F
Shear (1000g):	112 minutes

---

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

**Typical Value**

Basis Weight:	41 #/3000 ft <sup>2</sup>
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

**Total Product Caliper:** 6.84 mils

**Product Basis Weight Per MMSI:** 238.53 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104*

*For samples or other questions please call your Sales Representative.*

**Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023