



PRODUCT DATA SHEET

Date: 04/16/2024

Spinnaker
 550 Summit Avenue
 Troy, Oh 45373
 800 543-9452

3.0 mil TC Matte White Polypropylene ** B-92 ** 50# liner

Item#: 0041923

Recommended Print Type(s) to Test	----- TRIMLESS PROGRAMS -----			
	Dist. Ctr	Length	Min. Width	Core
Thermal Transfer Films Flexo	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	10 K	4"	3"
	New York	5 K	3"	3"
	New York	10 K	4"	3"
	Atlanta	5 K	3"	3"
	Atlanta	10 K	4"	3"
	Chicago	5 K	3"	3"
	Chicago	10 K	4"	3"

Recommended for hand-applied applications only.

Facestock: 3.0 mil TC Matte White Polypropylene

A white, mineral-filled, biaxially-oriented polypropylene film for use in a variety of printing and converting applications where durability, strength, and superior printability are key. One side is matte with a special print-receptive coating and the other is a satin gloss. Its key attribute is excellent thermal transfer printability. It will not tear unless an edge is nicked. Outdoor durability is about 3 to 6 months, depending on climatic conditions.

	Typical Value
Basis Weight:	42.5 #/3300 ft ²
Caliper:	3.0 mils
Tensile MD/CD:	11352 / 17028 PSI
Elongation @ Break MD/TD:	131 / 34%
Opacity:	87%

Adhesive: B-92

An aggressive general-purpose removable adhesive with medium initial tack. It will act as a permanent on smooth surfaces over long time periods or when used with paper facestocks.

	Typical Value
Coat Weight:	15 #/3300 ft ²
Coat Weight:	22.2 grams/m ²

Caliper: .6 mils
Adhesion to Stainless Steel, oz. (90° Peel): 22 oz
Loop Tack, oz.: 41oz
Service Temperature: -40 to 200 °F
Minimum Application Temperature: 40 °F
Shear (1000g): 15 minutes

Release Liner: **50# liner** A bleached, calendered liner featuring higher tensile and tear properties than the 40# liner, making it an excellent liner for perforating, fan-folding, and edge-punching.

Typical Value
Basis Weight: 53 #/3000 ft²
Caliper: 3.2 mils
Tensile MD/CD: 48 / 26 #/inch
Tear MD/CD: 45 / 51 grams
Opacity: 74%

Total Product Caliper: 6.8 mils
Product Basis Weight Per MMSI: 243.79 #
Shelf Life: 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104
For samples or other questions please call your Sales Representative.*

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 04/11/2024