

## PRODUCT DATA SHEET

Date: 04/26/2024

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

## 2.6m White Pearlized BOPP Cover \*\* BP-164 \*\* 40# liner

Item#: 0049287

	TRIMLESS PROGRAMS		
Dist. C	tr Length	Min. Width	Core
Troy, Oh	io 5 K	3"	3"
Troy, Oh	io 10 K	4"	3"

Facestock: 2.6m White Pearlized BOPP Cover

A white, multi-layer, biaxially-oriented polypropylene film that is top-coated for ink receptivity. This product coated with an opaque cover-up barrier coating which improves opacity for applications requiring little to no show-through of underlying text or graphics. This product offers great printability across many primary and secondary print methods.

**Typical Value** 

 Basis Weight:
 32.2 #/3300 ft²

 Caliper:
 2.6 mils

Tensile MD/CD: 13050 / 29010 PSI

Elongation @ Break MD/TD: 150 / 50% Opacity: >95%

Adhesive: **BP-164** A general purpose hot melt adhesive with excellent quick-stick properties. This

adhesive exhibits excellent adhesion to a broad range of packaging surfaces and has improved die cutting and stripping attributes compared to other hot melt

rubber based adhesives.

**Typical Value** 

Coat Weight:  $14 \#/3300 \text{ ft}^2$ Coat Weight:  $20.72 \text{ grams/m}^2$ 

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 63 Loop Tack, oz.: 97

Service Temperature: -50 to 150 °F

Minimum Application Temperature: 40 °F

Shear (1000g): 456 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

**Typical Value** 

Basis Weight:  $41 \#/3000 \text{ ft}^2$  Caliper: 2.5 mils Tensile MD/CD: 34 / 21 #/inch Tear MD/CD: 34 / 36 grams Opacity: 69 max%

**Total Product Caliper:** 0 mils

Product Basis Weight Per MMSI: 0.00 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023