

## PRODUCT DATA SHEET

Date: 05/08/2024

Spinnaker

550 Summit Avenue Troy, Oh 45373 800 543-9452

## 2.6mil White Pearlized BOPP \*\* SFA<sup>TM</sup> (2020) \*\* 40# liner

Item#: 0049299

	TRIMLESS PROGRAMS				
	Dist. Ctr	Length	Min. Width	Core	
	Troy, Ohio	5 K	3"	3"	
	Troy, Ohio	10 K	4"	3"	
	Ontario, CA	5 K	3"	3"	
	Ontario, CA	10 K	4"	3"	
Facestock: 2.6mil White Pearlized BOPP	A white, multi-layer, biaxially-oriented polypropylene film				
	top-coated for ink receptivity. This product offers great				
	printability across many primary and secondary print methods.				
	This facestock is not recommended for fan-folding applications.				
	Typical Value	•			
Basis Weight:	32.2 #/3300 ft <sup>2</sup>				
Caliper:	2.6 mils				
Tensile MD/CD:	13053 / 29008 PSI				
Elongation @ Break MD/TD:	150 / 50%				
Opacity:	90%				

Adhesive: SFA™ (2020)A clear, general purpose, emulsion acrylic permanent adhesive designed for<br/>applications with film facestocks. SFA exhibits excellent ultimate adhesion to<br/>polyethylene, polypropylene and glass. Well suited for small, cylindrical<br/>labeling. Limited testing shows this adhesive to be glove friendly, but<br/>application testing is recommended.

Coat Weight:	13 #/3300 ft <sup>2</sup>	
Coat Weight:	19.24 grams/m <sup>2</sup>	
Caliper:	.6 mils	
Adhesion to Stainless Steel, oz. (90° Peel):	32	
Loop Tack, oz.:	50	
Service Temperature:	-40 to 240 °F	
Minimum Application Temperature:	15 °F	
Shear (1000g):	112 minutes	

Release Liner: 40# liner

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

## **Typical Value**

Basis Weight: Caliper: Tensile MD/CD: Tear MD/CD: Opacity: 41 #/3000 ft<sup>2</sup> 2.5 mils 34 / 21 #/inch 34 / 36 grams 69 max%

**Total Product Caliper:** 5.7 mils **Product Basis Weight Per MMSI:** 190.11 # **Shelf Life:** 12 month(s) when stored at 72° F, 50% RH For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023