



**PRODUCT DATA SHEET**

Date: 04/26/2024

**Spinnaker**  
 550 Summit Avenue  
 Troy, Oh 45373  
 800 543-9452

**ScanTherm-Poly™ 4.0 \*\* BC-20™ \*\* 40# liner**

Item#: 0048713

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	4"	3"
Atlanta	5 K	3"	3"
Atlanta	10 K	4"	3"
Chicago	5 K	3"	3"
Chicago	10 K	4"	3"

Facestock: **ScanTherm-Poly™ 4.0**

A top-coated, medium-to-high sensitivity, direct thermal polypropylene film facestock. This film demonstrates excellent environmental resistance and medium-to-high print speeds. Initial activation temperature (0.2 ODU) is 180 degrees F.

Basis Weight:  
 Caliper:

**Typical Value**  
 53 #/3300 ft<sup>2</sup>  
 4.1 mils

Adhesive: **BC-20™**

A cold temperature hot melt adhesive featuring excellent adhesion to a variety of packaging materials and other substrates over a wide temperature range. It displays good die cutting and stripping characteristics. This adhesive performs well on wet and oily/greasy applications.

Coat Weight:  
 Coat Weight:  
 Caliper:  
 Adhesion to Stainless Steel, oz. (90° Peel):  
 Loop Tack, oz.:  
 Service Temperature:  
 Minimum Application Temperature:  
 Shear (1000g):

**Typical Value**  
 14 #/3300 ft<sup>2</sup>  
 20.72 grams/m<sup>2</sup>  
 .6 mils  
 38  
 72  
 -50 to 145 °F  
 10 °F  
 157 minutes

---

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

	<b>Typical Value</b>
Basis Weight:	41 #/3000 ft <sup>2</sup>
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

**Total Product Caliper:** 7.2 mils

**Product Basis Weight Per MMSI:** 236.00 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104*

*For samples or other questions please call your Sales Representative.*

**Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023