

## PRODUCT DATA SHEET

Date: 04/30/2025

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

Ultra Matte<sup>TM</sup> Litho \*\* B-92 \*\* 40# liner

Item#: 0041721

Brightness:

Recommended Print Type(s) to Test  Domino (UV Inkjet)  EFI™ Jetrion® (UV Inkjet)  Flexo	TRIMLESS PROGRAMS			
	Dist. Ctr	Length	Min. Width	Core
	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	2.5 K	3"	3"
	Chicago	5 K	3"	3"
	Chicago	2.5 K	3"	3"

Recommended for hand-applied applications only.

Facestock: **Ultra Matte**<sup>TM</sup> **Litho** A premium, matte-coated paper featuring superior smudge

resistance, high brightness and high opacity. This sheet offers

great ink receptivity, and can also be laser printed.

**Typical Value** 

60 #/3300 ft<sup>2</sup> Basis Weight: Caliper: 3.7 mils Tensile MD/CD: 35 / 17 Gloss: 10% Tear MD/CD: 50 / 55 grams Opacity: 91% **Sheffield Smoothness:** 30 SFU Parker Print: 2.8 microns

Adhesive: **B-92**An aggressive general-purpose removable adhesive with medium initial tack. It

89%

will act as a permanent on smooth surfaces over long time periods or when used

with paper facestocks.

**Typical Value** 

Coat Weight:  $15 \#/3300 \text{ ft}^2$ Coat Weight:  $22.2 \text{ grams/m}^2$ 

Caliper: .6 mils
Adhesion to Stainless Steel, oz. (90° Peel): 22 oz
Loop Tack, oz.: 41oz

Service Temperature: -40 to 200 °F

40 °F Minimum Application Temperature: Shear (1000g): 15 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

**Typical Value** 

41 #/3000 ft<sup>2</sup> Basis Weight: Caliper: 2.5 mils Tensile MD/CD: 34 / 21 #/inch Tear MD/CD: 34 / 36 grams Opacity: 69 max%

**Total Product Caliper:** 6.8 mils

Product Basis Weight Per MMSI: 252.84 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 09/04/2019