



PRODUCT DATA SHEET

Date: 12/01/2020

Spinnaker Coating
518 East Water Street
Troy, Oh 45373
800 543-9452

3mil UltraMatte Polypropylene ** SFA™ ** 40# liner

Item#: 0048278

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	4"	3"
Atlanta	5 K	3"	3"
Atlanta	10 K	4"	3"
Chicago	5 K	3"	3"
Chicago	10 K	4"	3"
Los Angeles	5 K	3"	3"
Los Angeles	10 K	4"	3"

Facestock: **3mil UltraMatte Polypropylene**

A top-coated, matte white polypropylene for use in a variety of applications. This facestock offers excellent printability on for flexo and thermal transfer printed variable labels. It is suitable for both indoor and outdoor labels up to 12 month outdoor life with the appropriate adhesive.

Basis Weight:

Typical Value

40.5 #/3300 ft²

Caliper:

3 mils

Tensile MD/CD:

14503 / 23206 PSI

Elongation @ Break MD/TD:

140 / 145%

Opacity:

87%

Adhesive: **SFA™**

A clear, general purpose, emulsion acrylic permanent adhesive designed for applications with film facestocks. SFA exhibits excellent ultimate adhesion to polyethylene, polypropylene and glass. Well suited for small, cylindrical labeling and is glove friendly.

Typical Value

Coat Weight:

13 #/3300 ft²

Coat Weight:

19.24 grams/m²

Caliper:

.6 mils

Adhesion to Stainless Steel, oz. (90° Peel):

27

Loop Tack, oz.:

33

Service Temperature:

-40 to +200 °F

Minimum Application Temperature:

40 °F

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Typical Value

Basis Weight:	41 #/3000 ft ²
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

Total Product Caliper: 6.1 mils

Product Basis Weight Per MMSI: 207.58 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Coating, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Coating, LLC. Because of the variety of possible applications for Spinnaker Coating's products and the continuing development of new applications, all Spinnaker Coating, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Coating, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/05/2020