

PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker

550 Summit Avenue Troy, Oh 45373 800 543-9452

3.0 mil TC Matte White Polypropylene ** BP-164 ** 40# liner

Item#: 0043514

	TRIMLESS PROGRAMS				
Recommended Print Type(s) to Test	Dist. Ctr	Length	Min. Width	Core	
Thermal Transfer Films	Troy, Ohio	5 K	3"	3"	
Flexo	Troy, Ohio	10 K	4"	3"	
	Chicago	5 K	3"	3"	
	Chicago	10 K	4"	3"	
Facestock: 3.0 mil TC Matte White Polypropylene	A white, mineral-filled, biaxially-oriented polypropylene film for				
	use in a variety of printing and converting applications where				
	durability, strength, and superior printability are key. One side is				
	matte with a special print-receptive coating and the other is a satin				
			ellent thermal transfer		
	will not tear unless an edge is nicked. Outdoor durability is about				
	3 to 6 months,	3 to 6 months, depending on climatic conditions.			
	Typical Value				
Basis Weight:	42.5 #/3300 ft ²				
Caliper:	3.0 mils				
Tensile MD/CD:	11352 / 17028 PSI				
Elongation @ Break MD/TD:	131 / 34%				
Opacity:	87%				

Adhesive: BP-164	A general purpose hot melt adhesive with excellent quick-stick properties. This adhesive exhibits excellent adhesion to a broad range of packaging surfaces and has improved die cutting and stripping attributes compared to other hot melt rubber based adhesives.			
Coat Weight: Coat Weight:	Typical Value 14 #/3300 ft ² 20.72 grams/m ²			

Coat Weight:20.72 grams/rCaliper:.6 milsAdhesion to Stainless Steel, oz. (90° Peel):63Loop Tack, oz.:97Service Temperature:-50 to 150 °FMinimum Application Temperature:40 °FShear (1000g):456 minutes

Release Liner: 40# liner

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Basis Weight: Caliper: Tensile MD/CD: Tear MD/CD: Opacity: **Typical Value** 41 #/3000 ft² 2.5 mils 34 / 21 #/inch 34 / 36 grams 69 max%

Total Product Caliper: 6.1 mils **Product Basis Weight Per MMSI:** 213.89 # **Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023