

## **PRODUCT DATA SHEET**

Date: 05/02/2024

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

## 1.5 mil Transparent Polystyrene \*\* B-122<sup>TM</sup>F \*\* 40# liner

Item#: 0041899

100111111111111111111111111111111111111				
	TRIMLESS PROGRAMS			
Recommended Print Type(s) to Test	Dist. Ctr	Length	Min. Width	Core
Flexo	Troy, Ohio	5 K	3"	3"
	Troy, Ohio	10 K	4"	3"
Facestock: 1.5 mil Transparent Polystyrene	A clear, rigid film used for prime label applications. This product is corona-treated for better printing and is appropriate for coupon technology.			
	Typical Value			
Basis Weight:	27 #/3300 ft <sup>2</sup>			
Caliper:	1.5 mils			
Tensile MD/CD:	10,500 / 10,500 PSI			
Elongation @ Break MD/TD:	45 / 40%			
Gloss:	165 / N/A%			
Surface Energy:	60 dynes/cm			

Adhesive: **B-122**<sup>TM</sup>**F** A clear all temperature acrylic adhesive featuring excellent adhesion to a variety

of surfaces with film facestocks. It covers a broad temperature range and has excellent converting characteristics on press. The high initial tack of B-122F to low surface energy polyolefins makes it an ideal for blow on applications

**Typical Value** 

Coat Weight:  $13 \#/3300 \text{ ft}^2$ Coat Weight:  $19.24 \text{ grams/m}^2$ 

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 24 Loop Tack, oz.: 47

Service Temperature: -65 to 200 °F Minimum Application Temperature: -10 °F Shear (1000g): 75 minutes Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

**Typical Value** 

 Basis Weight:
 41 #/3000 ft²

 Caliper:
 2.5 mils

 Tensile MD/CD:
 34 / 21 #/inch

 Tear MD/CD:
 34 / 36 grams

 Opacity:
 69 max%

**Total Product Caliper:** 4.6 mils

**Product Basis Weight Per MMSI:** 179.16 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023