

PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker

550 Summit Avenue Troy, Oh 45373 800 543-9452

High Gloss ** ATPTM ** 40# liner

Item#: 0043576

| | TRIMLESS PROGRAMS | | | |
|---|---|--------|------------|------|
| Recommended Print Type(s) to Test | Dist. Ctr | Length | Min. Width | Core |
| Domino (UV Inkjet) Xeikon (toner) Flexo | Troy, Ohio | 2.5 K | 3" | 3" |
| | Troy, Ohio | 5 K | 3" | 3" |
| | Chicago | 2.5 K | 3" | 3" |
| | Chicago | 5 K | 3" | 3" |
| | Ontario, CA | 2.5 K | 3" | 3" |
| | Ontario, CA | 5 K | 3" | 3" |
| Facestock: High Gloss | A cast coated paper featuring a mirror finish; ideal for a wide variety of printing technologies. | | | |

Basis Weight: Caliper: Tensile MD/CD: Gloss: Tear MD/CD: Opacity: Parker Print: Brightness:

Typical Value

57 #/3300 ft² 3.7 mils 29 / 16.5 90% 55 / 60 grams 90% .4 microns 87%

An all-temperature permanent acrylic adhesive suitable for a wide variety of applications with paper facestocks providing exceptional converting characteristics that allow stripping of intricate die patterns as well as wide-web, high-speed processing.

Typical Value

| Coat Weight: | 15 #/3300 ft ² | |
|--|---------------------------|--|
| Coat Weight: | 22.2 grams/m ² | |
| Caliper: | .6 mils | |
| Adhesion to Stainless Steel, oz. (90° Peel): | 20 | |
| Loop Tack, oz.: | 41 | |
| Service Temperature: | -65 to 200 °F | |
| Minimum Application Temperature: | -20 °F | |
| Shear (1000g): | 61 minutes | |

Release Liner: 40# liner

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Basis Weight: Caliper: Tensile MD/CD: Tear MD/CD: Opacity: **Typical Value** 41 #/3000 ft² 2.5 mils 34 / 21 #/inch 34 / 36 grams 69 max%

Total Product Caliper: 6.8 mils **Product Basis Weight Per MMSI:** 246.53 # **Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 09/11/2024