

PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

Smudgeproof Kimdura® FPG-80 ** B-82 ** 50# liner

Item#: 0043145

Opacity:

	TRIMLESS PROGRAMS			
Recommended Print Type(s) to Test Impact Films Thermal Transfer Films Flexo	Dist. Ctr Troy, Ohio Chicago	Length 5 K 5 K	Min. Width 3" 3"	Core 3" 3"
Facestock: Smudgeproof Kimdura® FPG-80	This film is a matte white, multi-layer polypropylene film top-coated to provide premium dot matrix and thermal transfer print images. Outdoor exposure is up to one year. Typical applications include shelf marking and container labeling. The product is no longer warranted for Flexographic or any non-thermal printing methods based on feedback from the facestock supplier. Not recommended for freezer applications.			
	Typical Value			
Basis Weight:	56 #/3300 ft ²			
Caliper:	3.8 mils			
Tensile MD/CD:	22 / 62 #/inch			
Elongation @ Break MD/TD:	89.9 / 16.1%			
	o =			

Adhesive: **B-82** A general purpose hot melt adhesive with excellent quick-stick properties and

95%

long-term adhesion to a broad range of surfaces.

Typical Value

Coat Weight: $14 \#/3300 \text{ ft}^2$ Coat Weight: 20.72 grams/m^2

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 60 Loop Tack, oz.: 94

Service Temperature: -50 to 150 °F Minimum Application Temperature: 40 °F Shear (1000g): 445 minutes

Release Liner: 50# liner A bleached, calendered liner featuring higher tensile and tear properties than the

40# liner, making it an excellent liner for perforating, fan-folding, and edge-

punching.

Typical Value

 Basis Weight:
 53 #/3000 ft²

 Caliper:
 3.2 mils

 Tensile MD/CD:
 48 / 26 #/inch

 Tear MD/CD:
 45 / 51 grams

Opacity: 74%

Total Product Caliper: 7.6 mils

Product Basis Weight Per MMSI: 270.11#

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023