



## PRODUCT DATA SHEET

Date: 12/12/2025

**Spinnaker**  
550 Summit Avenue  
Troy, Oh 45373  
800 543-9452

**60# Chartreuse Fluorescent (new 2019) \*\* SC-21 \*\* 40# liner**

Item#: 0049742

----- TRIMLESS PROGRAMS -----

| Dist. Ctr   | Length | Min. Width | Core |
|-------------|--------|------------|------|
| Troy, Ohio  | 2.5 K  | 3"         | 3"   |
| Troy, Ohio  | 5 K    | 3"         | 3"   |
| Troy, Ohio  | 10 K   | 4"         | 3"   |
| Chicago     | 2.5 K  | 3"         | 3"   |
| Chicago     | 5 K    | 3"         | 3"   |
| Chicago     | 10 K   | 4"         | 3"   |
| Ontario, CA | 2.5 K  | 3"         | 3"   |
| Ontario, CA | 5 K    | 3"         | 3"   |
| Ontario, CA | 10 K   | 4"         | 3"   |

Facestock: **60# Chartreuse Fluorescent (new 2019)**

A matte, neon bright sheet designed for high visibility and impact printing. This is an alkaline sheet.

### Typical Value

|                |                           |
|----------------|---------------------------|
| Basis Weight:  | 59 #/3300 ft <sup>2</sup> |
| Caliper:       | 4.0 mils                  |
| Tensile MD/CD: | 26 / 16 #/inch            |
| Tear MD/CD:    | 44 / 48 grams             |

Adhesive: **SC-21**

A robust hot-melt adhesive exhibiting excellent adhesion and quick tack to a broad range of surfaces over a wide application temperature range. It displays the superior converting characteristics of an acrylic and wide web converting is excellent.

### Typical Value

|  |                            |
|--|----------------------------|
| Coat Weight:                                 | 14 #/3300 ft <sup>2</sup>  |
| Coat Weight:                                 | 20.72 grams/m <sup>2</sup> |
| Caliper:                                     | .6 mils                    |
| Adhesion to Stainless Steel, oz. (90° Peel): | 48                         |
| Loop Tack, oz.:                              | 89                         |
| Service Temperature:                         | -50 to 140 °F              |
| Minimum Application Temperature:             | 25 °F                      |
| Shear (1000g):                               | 1078 minutes               |

---

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

**Typical Value**

|                |                           |
|----------------|---------------------------|
| Basis Weight:  | 41 #/3000 ft <sup>2</sup> |
| Caliper:       | 2.5 mils                  |
| Tensile MD/CD: | 34 / 21 #/inch            |
| Tear MD/CD:    | 34 / 36 grams             |
| Opacity:       | 69 max%                   |

**Total Product Caliper:** 7.1 mils

**Product Basis Weight Per MMSI:** 248.63 #

**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104*

*For samples or other questions please call your Sales Representative.*

**Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023