



PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker
550 Summit Avenue
Troy, Oh 45373
800 543-9452

Laser Latex ** ATP™ ** 3.5 mil (50#) LF

Item#: 0001495

----- TRIMLESS PROGRAMS -----				
Recommended Print Type(s) to Test	Dist. Ctr	Length	Min. Width	Core
Laser	Troy, Ohio	5 K	3"	6"
Flexo	Troy, Ohio	10 K	4"	6"
	Chicago	5 K	3"	6"
	Chicago	10 K	4"	6"

Facestock: **Laser Latex**

A C2S saturated paper designed to have excellent toner receptivity in a variety of laser printers, while offering the same strength and environmental properties of a typical latex sheet. Common applications include drum labeling and shelf marking.

Typical Value	
Basis Weight:	58.2 #/3300 ft ²
Caliper:	3.7 mils
Tensile MD/CD:	29.8 / 20.5 #/inch
Tear MD/CD:	45 / 45 grams
Opacity:	87%
Sheffield Smoothness:	60 SFU

Adhesive: **ATP™**

An all-temperature permanent acrylic adhesive suitable for a wide variety of applications with paper facestocks providing exceptional converting characteristics that allow stripping of intricate die patterns as well as wide-web, high-speed processing.

Typical Value	
Coat Weight:	15 #/3300 ft ²
Coat Weight:	22.2 grams/m ²
Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	20
Loop Tack, oz.:	41
Service Temperature:	-65 to 200 °F
Minimum Application Temperature:	-20 °F
Shear (1000g):	61 minutes

Release Liner: **3.5 mil (50#) LF**

The 3.5mil layflat is a bleached white, MG liner designed specifically to be compatible with high and medium speed cut-sheet laser and ink jet printers. This product is well suited for applications requiring a high degree of layflat. A small amount of clay is applied to the backside of the paper to enhance printability.

Typical Value

Basis Weight:	50 #/3000 ft ²
Caliper:	3.5 mils
Tensile MD/CD:	35 / 14 #/inch
Tear MD/CD:	50 / 75 grams
Opacity:	89%

Total Product Caliper: 7.8 mils

Product Basis Weight Per MMSI: 269.89 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023