

PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

45# CTT ** GPRTM Removable ** 40# liner

Item#: 0045360

| Recommended Print Type(s) to Test Screen Americas (UV Inkjet) Thermal Transfer Papers Flexo | TRIMLESS PROGRAMS | | | |
|---|-------------------|--------|------------|------|
| | Dist. Ctr | Length | Min. Width | Core |
| | Troy, Ohio | 5 K | 3" | 3" |
| | Troy, Ohio | 10 K | 4" | 3" |
| | Ontario, CA | 5 K | 3" | 3" |
| | Ontario, CA | 10 K | 4" | 3" |

Recommended for hand-applied applications only.

Facestock: 45# CTT A premium, coated sheet that has excellent thermal transfer

imaging with a wide range of ribbons, and superior flexo

printability.

Typical Value

 Basis Weight:
 45 #/3300 ft²

 Caliper:
 3.0 mils

 Tensile MD/CD:
 27 / 17

 Tear MD/CD:
 42 / 45 grams

 Opacity:
 88%

Opacity: 88% Brightness: 87%

Adhesive: **GPR**TM **Removable** A general purpose removable adhesive designed to remove cleanly from a wide

variety of substrates. It is engineered to give excellent tack with minimal building of adhesion over time from a variety of surfaces. It is appropriate for

laser applications.

Typical Value

Coat Weight: $15 \#/3300 \text{ ft}^2$ Coat Weight: 22.2 grams/m^2

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 13

Loop Tack, oz.: 24

Service Temperature: -40 to 200 °F

Minimum Application Temperature: 40 °F Shear (1000g): 35 minutes Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Typical Value

41 #/3000 ft² Basis Weight: Caliper: 2.5 mils Tensile MD/CD: 34 / 21 #/inch Tear MD/CD: 34 / 36 grams Opacity: 69 max%

Total Product Caliper: 6.1 mils **Product Basis Weight Per MMSI:** 221.26 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 09/27/2024