



PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker
550 Summit Avenue
Troy, Oh 45373
800 543-9452

3.3 mil Durable Polypropylene ** B-122™F ** 40# liner

Item#: 0041896

----- TRIMLESS PROGRAMS -----				
Recommended Print Type(s) to Test	Dist. Ctr	Length	Min. Width	Core
Domino (UV Inkjet)	Troy, Ohio	5 K	3"	3"
Durst US (UV inkjet)	Troy, Ohio	2.5 K	3"	3"
EFI™ Jetrion® (UV Inkjet)	Troy, Ohio	10 K	4"	3"
Impact Films				
Screen Americas (UV Inkjet)				
Thermal Transfer Films				
Flexo				
Facestock: 3.3 mil Durable Polypropylene		A top coated matte white, biaxially-oriented polypropylene film suitable for outdoor applications of up to two years. It is appropriate for use where durability, strength, and superior thermal transfer or dot matrix printability are key.		
		Typical Value		
Basis Weight:		40.0 #/3300 ft²		
Caliper:		3.3 mils		
Tensile MD/CD:		14,500 / 13,000 PSI		
Elongation @ Break MD/TD:		50 / 60%		
Opacity:		91%		
Adhesive: B-122™F		A clear all temperature acrylic adhesive featuring excellent adhesion to a variety of surfaces with film facestocks. It covers a broad temperature range and has excellent converting characteristics on press. The high initial tack of B-122F to low surface energy polyolefins makes it an ideal for blow on applications		
		Typical Value		
Coat Weight:		13 #/3300 ft²		
Coat Weight:		19.24 grams/m²		
Caliper:		.6 mils		
Adhesion to Stainless Steel, oz. (90° Peel):		24		
Loop Tack, oz.:		47		
Service Temperature:		-65 to 200 °F		
Minimum Application Temperature:		-10 °F		
Shear (1000g):		75 minutes		

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Typical Value

Basis Weight:	41 #/3000 ft ²
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

Total Product Caliper: 6.4 mils

Product Basis Weight Per MMSI: 206.53 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023