



PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker
550 Summit Avenue
Troy, Oh 45373
800 543-9452

3.3 mil Durable Polypropylene ** C-122F ** 50# liner

Item#: 0041909

----- TRIMLESS PROGRAMS -----				
Recommended Print Type(s) to Test	Dist. Ctr	Length	Min. Width	Core
Domino (UV Inkjet)	Troy, Ohio	2.5 K	3"	3"
Durst US (UV inkjet)	Troy, Ohio	5 K	3"	3"
EFI™ Jetrion® (UV Inkjet)	Troy, Ohio	10 K	3"	3"
Impact Films	New York	2.5 K	3"	3"
Screen Americas (UV Inkjet)	New York	5 K	3"	3"
Thermal Transfer Films	New York	10 K	3"	3"
Flexo	Atlanta	2.5 K	3"	3"
	Atlanta	5 K	3"	3"
	Atlanta	10 K	4"	3"
	Chicago	2.5 K	3"	3"
	Chicago	5 K	3"	3"
	Chicago	10 K	4"	3"
	Ontario, CA	2.5 K	3"	3"
	Ontario, CA	5 K	3"	3"
	Ontario, CA	10 K	4"	3"

This face/adhesive combination conforms to BS5609: 1986 Section 2 and Section 3 - 'Maritime and Laboratory Performance of Label Base Materials for drum labelling.

Facestock: 3.3 mil Durable Polypropylene

A top coated matte white, biaxially-oriented polypropylene film suitable for outdoor applications of up to two years. It is appropriate for use where durability, strength, and superior thermal transfer or dot matrix printability are key.

Basis Weight:

Typical Value

40.0 #/3300 ft²

Caliper:

3.3 mils

Tensile MD/CD:

14,500 / 13,000 PSI

Elongation @ Break MD/TD:

50 / 60%

Opacity:

91%

Adhesive: C-122F

A premium drum and barrel acrylic adhesive for film facestocks that provides excellent adhesion to painted metal, polyolefin and fiber drums in all weather conditions. As a heavy coat weight of B-122F, It is well suited for the most

demanding of label applications.

	Typical Value
Coat Weight:	18 #/3300 ft ²
Coat Weight:	26.64 grams/m ²
Caliper:	.8 mils
Adhesion to Stainless Steel, oz. (90° Peel):	32.1oz
Loop Tack, oz.:	32.6 oz
Service Temperature:	-65 to 200 °F
Minimum Application Temperature:	-10 °F
Shear (1000g):	82 minutes

Release Liner: 50# liner	A bleached, calendered liner featuring higher tensile and tear properties than the 40# liner, making it an excellent liner for perforating, fan-folding, and edge-punching.
---------------------------------	---

	Typical Value
Basis Weight:	53 #/3000 ft ²
Caliper:	3.2 mils
Tensile MD/CD:	48 / 26 #/inch
Tear MD/CD:	45 / 51 grams
Opacity:	74%

Total Product Caliper: 7.3 mils

Product Basis Weight Per MMSI: 244.84 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

