



PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker
550 Summit Avenue
Troy, Oh 45373
800 543-9452

2.4m White Pearlized BOPP ** VG-325 ** 1.2 mil Clear Polyester

Item#: 0048992

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"
Chicago	10 K	4"	3"
Ontario, CA	2.5 K	3"	3"
Ontario, CA	5 K	3"	3"
Ontario, CA	10 K	4"	3"

Facestock: **2.4m White Pearlized BOPP**

A top coated white polypropylene film with a pearlized appearance. This product offers excellent flexo printability. We have also had success with thermal transfer printing using resin and wax/resin ribbons, but testing is recommended with your specific printer and ribbon combinations as it is not warranted as such. This component is not available for custom constructions.

Typical Value

Basis Weight:	30 #/3300 ft ²
Caliper:	2.4 mils
Gloss:	95 / N/A%
Opacity:	89%

Adhesive: **VG-325**

A general purpose permanent emulsion acrylic adhesive that offers excellent adhesion. This component is not available for custom constructions.

Typical Value

Coat Weight:	13.5 #/3300 ft ²
Coat Weight:	19.98 grams/m ²
Caliper:	.4 mils
Adhesion to Stainless Steel, oz. (90° Peel):	33
Loop Tack, oz.:	39
Service Temperature:	-40 to 248 °F
Minimum Application Temperature:	25 °F

Release Liner: 1.2 mil Clear Polyester

A 1.2 mil clear polyester liner is designed for roll label applications where smoothness, cleanliness, aesthetics and the strength properties of the liner are emphasized. This liner is coated with a premium release system designed for the reliable dispensing of film products. This component is not available for custom constructions.

Typical Value

Basis Weight:

28.3 #/3000 ft²

Caliper:

1.18 mils

Tensile MD/CD:

22,700 / 19,900 #/inch

Total Product Caliper: 3.98 mils**Product Basis Weight Per MMSI:** 157.12 #**Shelf Life:** 12 month(s) when stored at 72° F, 50% RH*For application recommendations call 877-210-5104**For samples or other questions please call your Sales Representative.***Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 09/20/2024