

## PRODUCT DATA SHEET

Date: 05/01/2024

**Spinnaker** 550 Summit Avenue Troy, Oh 45373 800 543-9452

## Veero<sup>TM</sup> 54# Semi Gloss \*\* VA-365 \*\* Veero 40# Liner

Item#: 0048344

Brightness:

TRIMLESS PROGRAMS			
Dist. Ctr	Length	Min. Width	Core
New York	2.5 K	3"	3"
New York	5 K	3"	3"
New York	10 K	4"	3"
Atlanta	2.5 K	3"	3"
Atlanta	5 K	3"	3"
Atlanta	10 K	4"	3"
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"
Chicago	10 K	4"	3"
Ontario, CA	2.5 K	3"	3"
Ontario, CA	5 K	3"	3"
Ontario CA	10 K	<b>4</b> "	3"

Facestock: Veero<sup>TM</sup> 54# Semi Gloss

A bright white, semi gloss litho with excellent strength characteristics. This sheet is printable with UV and water-based flexo, and UV letterpress inks. The lower basis weight creates an economical sheet, without sacrificing quality. This component is not available for custom constructions.

## **Typical Value**

 Basis Weight:
 54.0 #/3300 ft²

 Caliper:
 2.9 mils

 Tensile MD/CD:
 28 / 15 #/inch

 Gloss:
 67%

 Tear MD/CD:
 45 / 55 grams

 Opacity:
 85.5%

 Sheffield Smoothness:
 18 SFU

Adhesive: VA-365 An economical all-temperature acrylic adhesive choice for a wide range of

89.8%

application temperatures. This component is not available for custom

constructions.

**Typical Value** 

Coat Weight:  $12.5 \#/3300 \text{ ft}^2$ 

Coat Weight: 18.5 grams/m<sup>2</sup>

.4 mils Caliper: Adhesion to Stainless Steel, oz. (90° Peel): Loop Tack, oz.: 50

Service Temperature: -65 to 200 °F -20 °F Minimum Application Temperature:

Release Liner: Veero 40# Liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

**Typical Value** 

39 #/3000 ft<sup>2</sup> Basis Weight: Caliper: 2.4 mils Tensile MD/CD: 33 / 16 #/inch Tear MD/CD: 26 / 36 grams

Opacity: 60%

**Total Product Caliper:** 5.7 mils Product Basis Weight Per MMSI: 230.32 #

**Shelf Life:** 12 month(s) when stored at 72° F. 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

## **Important Notice**

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(\*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products. LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/23/2023