



PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker
550 Summit Avenue
Troy, Oh 45373
800 543-9452

2.6mil White Pearlized BOPP ** B-122™F ** 40# liner

Item#: 0050348

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	3"	3"

Facestock: 2.6mil White Pearlized BOPP

A white, multi-layer, biaxially-oriented polypropylene film that is top-coated for ink receptivity. This product offers great printability across many primary and secondary print methods. This facestock is not recommended for fan-folding applications.

Typical Value

Basis Weight:	32.2 #/3300 ft ²
Caliper:	2.6 mils
Tensile MD/CD:	13053 / 29008 PSI
Elongation @ Break MD/TD:	150 / 50%
Opacity:	90%

Adhesive: B-122™F

A clear all temperature acrylic adhesive featuring excellent adhesion to a variety of surfaces with film facestocks. It covers a broad temperature range and has excellent converting characteristics on press. The high initial tack of B-122F to low surface energy polyolefins makes it an ideal for blow on applications

Typical Value

Coat Weight:	13 #/3300 ft ²
Coat Weight:	19.24 grams/m ²
Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	24
Loop Tack, oz.:	47
Service Temperature:	-65 to 200 °F
Minimum Application Temperature:	-10 °F
Shear (1000g):	75 minutes

Release Liner: **40# liner**

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

	Typical Value
Basis Weight:	41 #/3000 ft ²
Caliper:	2.5 mils
Tensile MD/CD:	34 / 21 #/inch
Tear MD/CD:	34 / 36 grams
Opacity:	69 max%

Total Product Caliper: 5.7 mils

Product Basis Weight Per MMSI: 190.11 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 06/27/2024