

PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

Tyvek® 1073-D ** B-122TMF ** 50# liner

Item#: 0041916

| Recommended Print Type(s) to Test | TRIMLESS PROGRAMS | | | |
|-----------------------------------|-------------------|--------|------------|------|
| | Dist. Ctr | Length | Min. Width | Core |
| Flexo | Troy, Ohio | 2.5 K | 3" | 3" |
| | Troy, Ohio | 5 K | 3" | 3" |
| | Troy, Ohio | 10 K | 4" | 3" |
| | Chicago | 2.5 K | 3" | 3" |
| | Chicago | 5 K | 3" | 3" |
| | Chicago | 10 K | 4" | 3" |
| | Ontario, CA | 2.5 K | 3" | 3" |
| | Ontario, CA | 5 K | 3" | 3" |
| | Ontario, CA | 10 K | 4" | 3" |

Facestock: **Tyvek**® **1073-D**A high strength, white, spun-bound polyolefin used where tear resistance is required.

Typical Value

Basis Weight: $50 \#/3300 \text{ ft}^2$ Caliper: 8 mils Tensile MD/CD: 47 / 48 PSI

Adhesive: **B-122**TM**F** A clear all temperature acrylic adhesive featuring excellent adhesion to a variety

of surfaces with film facestocks. It covers a broad temperature range and has excellent converting characteristics on press. The high initial tack of B-122F to low surface energy polyolefins makes it an ideal for blow on applications

Typical Value

Coat Weight: $13 \#/3300 \text{ ft}^2$ Coat Weight: 19.24 grams/m^2

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 24 Loop Tack, oz.: 47

Service Temperature: -65 to 200 °F Minimum Application Temperature: -10 °F Shear (1000g): 75 minutes Release Liner: 50# liner A bleached, calendered liner featuring higher tensile and tear properties than the

40# liner, making it an excellent liner for perforating, fan-folding, and edge-

punching.

Typical Value

Basis Weight: $53 \#/3000 \text{ ft}^2$ Caliper: 3.2 mils Tensile MD/CD: 48 / 26 #/inch Tear MD/CD: 45 / 51 grams

Opacity: 74%

Total Product Caliper: 11.8 mils

Product Basis Weight Per MMSI: 255.37 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104 For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 09/29/2023