



PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker
550 Summit Avenue
Troy, Oh 45373
800 543-9452

SafeTE™ Cover-up Film ** B-82 ** 50# liner

Item#: 0043158

Recommended Print Type(s) to Test		----- TRIMLESS PROGRAMS -----			
Flexo		Dist. Ctr	Length	Min. Width	Core
		Troy, Ohio	2.5 K	3"	3"
		Troy, Ohio	5 K	3"	3"
Facestock: SafeTE™ Cover-up Film		A biaxially-oriented, multi-layer polypropylene film that features tamper evident properties. It is coated with an opaque cover-up barrier coating which improves opacity for applications requiring little to no show-through of underlying text or graphics. This face is flexo printable and may be thermal transfer printed if ribbon / substrate combination has been tested for specific performance needs. Primer is recommended when using UV Flexo inks.			
		Typical Value			
Basis Weight:		26.4 #/3300 ft ²			
Caliper:		3.8 mils			
Tensile MD/CD:		22 / 62 #/inch			
Elongation @ Break MD/TD:		89.9 / 16.1%			
Opacity:		>95%			
Adhesive: B-82		A general purpose hot melt adhesive with excellent quick-stick properties and long-term adhesion to a broad range of surfaces.			
		Typical Value			
Coat Weight:		14 #/3300 ft ²			
Coat Weight:		20.72 grams/m ²			
Caliper:		.6 mils			
Adhesion to Stainless Steel, oz. (90° Peel):		60			
Loop Tack, oz.:		94			
Service Temperature:		-50 to 150 °F			
Minimum Application Temperature:		40 °F			
Shear (1000g):		445 minutes			

Release Liner: **50# liner**

A bleached, calendered liner featuring higher tensile and tear properties than the 40# liner, making it an excellent liner for perforating, fan-folding, and edge-punching.

Typical Value

Basis Weight:	53 #/3000 ft ²
Caliper:	3.2 mils
Tensile MD/CD:	48 / 26 #/inch
Tear MD/CD:	45 / 51 grams
Opacity:	74%

Total Product Caliper: 7.6 mils

Product Basis Weight Per MMSI: 207.79 #

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

For application recommendations call 877-210-5104

For samples or other questions please call your Sales Representative.

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/24/2023