

PRODUCT DATA SHEET

Date: 04/30/2025

Spinnaker 550 Summit Avenue Troy, Oh 45373 800 543-9452

60# Green Fluorescent (new 2018) ** SC-21 ** 40# liner

Item#: 0049740

TRIMLESS PROGRAMS			
Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	2.5 K	3"	3"
Troy, Ohio	5 K	3"	3"
Troy, Ohio	10 K	4"	3"
New York	2.5 K	3"	3"
New York	5 K	3"	3"
New York	10 K	4"	3"
Atlanta	2.5 K	3"	3"
Atlanta	5 K	3"	3"
Atlanta	10 K	4"	3"
Chicago	2.5 K	3"	3"
Chicago	5 K	3"	3"
Chicago	10 K	4"	3"
Ontario, CA	2.5 K	3"	3"
Ontario, CA	5 K	3"	3"
Ontario, CA	10 K	4"	3"

Facestock: 60# Green Fluorescent (new 2018)

A matte, neon bright sheet designed for high visibility and impact printing. This is an alkaline sheet.

Typical Value

 $\begin{array}{lll} \text{Basis Weight:} & 60 \, \#/3300 \, \text{ft}^2 \\ \text{Caliper:} & 3.8 \, \text{mils} \\ \text{Tensile MD/CD:} & 27 \, / \, 14 \, \#/\text{inch} \\ \text{Tear MD/CD:} & 48 \, / \, 52 \, \text{grams} \\ \end{array}$

Adhesive: SC-21 A robust hot-melt adhesive exhibiting excellent adhesion and quick tack to a

broad range of surfaces over a wide application temperature range. It displays the superior converting caracteristics of an acrylic and wide web converting is

excellent.

Typical Value

Coat Weight: $14 \#/3300 \text{ ft}^2$ Coat Weight: 20.72 grams/m^2

Caliper: .6 mils Adhesion to Stainless Steel, oz. (90° Peel): 48 Loop Tack, oz.: 89 Service Temperature: -50 to 140 °F

25 °F Minimum Application Temperature:

Shear (1000g): 1078 minutes

Release Liner: 40# liner A bleached, calendered liner featuring excellent die cutting and stripping

characteristics. Recommended for use in roll-to-roll applications.

Typical Value

41 #/3000 ft² Basis Weight: Caliper: 2.5 mils Tensile MD/CD: 34 / 21 #/inch Tear MD/CD: 34 / 36 grams Opacity: 69 max%

For application recommendations call 877-210-5104 **Total Product Caliper:** 6.9 mils For samples or other questions please call your Sales Representative.

Product Basis Weight Per MMSI: 250.74#

Shelf Life: 12 month(s) when stored at 72° F, 50% RH

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All trademarks are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Pressure Sensitive Products, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Pressure Sensitive Products, LLC. Because of the variety of possible applications for Spinnaker's products and the continuing development of new applications, all Spinnaker Pressure Sensitive Products, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Pressure Sensitive Products, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 05/22/2023